



## Baysilone® LSR4030

*Liquid Silicone Rubber*

### Product Description

Baysilone® LSR 4030 liquid silicone rubber is a two-component product formulated for use in liquid injection molding to produce high performance elastomeric parts. It is transparent, but easily pigmentable using Momentive Performance Materials LIM color masterbatches. Baysilone® LSR 4030 offers convenient 1:1 mix ratio and rapid cure time for manufacturing productivity.

### Key Performance Properties

- | High clarity for excellent visibility
- | High tensile strength
- | Convenient 1:1 mix ratio for use with automatic equipment
- | Rapid cure time depending upon part size, configuration, and molding temperature
- | Excellent release from metal molds

Viscosity in cps at shear gradient $\gamma = 10s^{-1}$	400,000
Density in g/cm <sup>3</sup>	1.11
Appearance	transparent
Pot-life at room temperature 68°F / closed vessel	3 days

### Typical Properties Data

#### TYPICAL PRODUCT DATA

Mechanical properties of Baysilone LSR were obtained from standard 2-mm thick molded sheets using the following process parameters:

A/B Blend Ratio		1/1
Molding Conditions		10 minutes @ 175°C
Post Bake Conditions		4 hours @ 200°C
		<b>Post-cured 4 hr/200°C (392°F)</b>
Shore A hardness		33
Tensile strength	psi	1160
	MPa	8.0
Elongation at break	%	700
Tear Strength	ppi	100
	N/mm	17.5
Compression set 22 h/175°C	%	15

The dielectric properties were determined on specimens cured for 10 minutes at 175°C and postcured for 4 hours at 200°C.

Volume resistivity	$\Omega \cdot \text{cm}$	1E 16
Dielectric strength	kV/mm	24
Dielectric constant	$\epsilon_r$ 50 Hz	3.3

Dissipation factor	$\tan \delta / 50 \text{ Hz}$	0.0025
--------------------	-------------------------------	--------

**Specifications**

Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive Performance Materials at 800/255-8886.

**USP CLASS VI STATUS:**

LSR4030 meets the requirements for biocompatibility for USP Class VI Plastics and ISO 10993, Part 1 testing requirements for less than 30 days human contact time. Compliance is based on testing a single batch which is considered representative of production. It is the responsibility of the end-user to verify compliance of the final fabricated product. Questions on the above testing should be directed to the Product Regulatory Department of Momentive Performance Materials. The user has sole responsibility for determining the suitability of this product for any application.

**Handling and Safety**

Material Safety Data Sheets are available upon request from Momentive Performance Materials. Similar information for solvents and other chemicals used with Momentive Performance Materials products should be obtained from your suppliers. When solvents are used, proper safety precautions must be observed.

**Storage & Warranty Period**

Baysilone LSR should be stored in a cool place. Stored in their original sealed containers, the separate components have a shelf life of at least six months. Containers which have been opened should be firmly sealed for storage.

**Availability**

Products may be ordered from Momentive Performance Materials, Waterford, NY, 12188, or the Momentive Performance Materials sales office nearest you.

**Government Requirement**

Prior to considering use of a Momentive Performance Materials product in fulfilling any Government requirement, please contact the Government and Trade Compliance office at (413) 448-4624.

®Baysilone is a licensed trademark of Momentive Performance Materials Silicones.

**LEGAL DISCLAIMER**

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS, THEIR SUBSIDIARIES OR AFFILIATES (THE "SUPPLIER"), ARE SOLD SUBJECT TO THE SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN APPLICABLE SALES AGREEMENTS, PRINTED ON THE BACK OF ACKNOWLEDGMENTS AND INVOICES, OR AVAILABLE UPON REQUEST. ALTHOUGH THE INFORMATION, RECOMMENDATIONS OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIER'S MATERIALS, PRODUCTS, SERVICES, RECOMMENDATIONS OR ADVICE. NOTHING IN THIS OR ANY OTHER DOCUMENT SHALL ALTER, VARY, SUPERSEDE OR OPERATE AS A WAIVER OF ANY OF THE SUPPLIER'S STANDARD CONDITIONS OF SALE.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's materials, products, services, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any material, product, service or design is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier or any of its subsidiaries or affiliated companies, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.