



# RTV12

## RTV12

### Description

RTV12 is a clear two-component, low viscosity potting compound that cures at room temperature to a soft pliable rubber. RTV12 will cure in deep sections without additional heating or moisture. RTV12 has been designed to achieve primerless adhesion to many substrates, including metals, plastics and ceramics, typical of those found in electronic assemblies.

RTV12C curing agent is mixed with RTV12A base compound producing a clear cured rubber to provide see-through properties in greater thicknesses. RTV12 allows visual observation of the components during pouring and easy identification, repair, and replacement of components when necessary.

RTV12 is suggested for evaluation as a potting material to provide environmental protection to electrical and electronic assemblies. When cured, the soft, rubbery property of RTV12 rubber cushions against mechanical shock and vibration. The excellent electrical properties make it a candidate material for both high and low voltage electrical assemblies.

### Key Features and Benefits

- Clear to allow easy identification of components
- Primerless adhesion to many metals and plastics
- Repairable • Room temperature cure
- Excellent electrical properties
- Can be used with materials that cause cure inhibition with other RTV's
- Specially formulated to minimize copper corrosion
- Easily flows in and around complex electronic assemblies
- Easy to use on production line may be mixed by hand or machine

### Typical Physical Properties

#### Uncured Properties As Supplied

	RTV12A Base Compound	RTV12C Curing Agent
Color	Clear, Slight Haze	Clear
Viscosity, cps	1300	15
Specific Gravity	1.00	0.84
Solvent	None	Mineral Spirits
Shelf life, months	6	6

#### Uncured Properties Curing Agent Added

	RTV12A with RTV12C
Base to Curing Agent Ratio by Weight	20:1
Catalyzed Viscosity @ 5 Min.	1500

## RTV12

Catalyzed Brookfield Viscosity @ 30 Min.	3200
Catalyzed Brookfield Viscosity @ 60 Min.	Gel
Gel Time, minutes @ 25C (77F)	100
Gel Time, minutes @ 85C (185F)	30
Durometer, Shore A @ 3 days	18
Specific Gravity	1.00

### Cured Properties

ASTM Sheet 1.9 mm (0.075 in.)thickness	24 hrs Press + 48 hrs @ 25°C (77°F) 50% R.H.
<b>Electrical</b>	
Dielectric Strength, volts/mil	400
Dielectric Constant, 1 kHz	3.0
Dissipation Factor, 1 kHz	0.001
Volume Resistivity, ohm-cm	$1 \times 10^{13}$
<b>Thermal</b>	
Useful Temperature Range	-60 to 204°C(-75 to 400°F)

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Product Safety, Handling and Storage

#### WARNING:

RTV12C curing agent will cause severe skin irritation and eye burns. Keep out of reach of children. Avoid contact with skin, eyes and clothing. If spilled on clothing, remove clothing at once and wash same before re-use. In case of contact, immediately flush skin or eyes with water for 15 minutes, and consult a physician.

RTV12C curing agent contains mineral spirits and is classified as flammable. Keep away from heat, sparks and flame

This product may be shipped at ambient temperatures up to 110°F for up to 7 days maximum. The warranty period is six months from date of shipment from Momentive Performance Materials if stored in the original unopened container at 25°C (77°F) or below. Keep curing agent container tightly closed. Avoid all unnecessary exposure to air and moisture such exposure may reduce the catalyst activity substantially and may adversely affect the cure rate and cured properties.

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### Processing Recommendations

#### Mixing Instructions

RTV12C curing agent is non-separating. However, shaking is suggested to insure uniformity.

## RTV12

RTV12A base compound is mixed with RTV12C curing agent in a 20:1 ratio by weight. The base compound and curing agent must be weighed and measured to insure the proper 20:1 blend ratio. Using less curing agent will result in a softer rubber after cure.

Thoroughly mix the RTV and the curing agent using clean tools. Scrape the side and bottom of the container several times to produce a homogeneous mixture. When using power mixers avoid excessive speeds which could entrap large amounts of air or cause overheating of the silicone and resultant shortening of work life.

### Deaeration

Air entrapped during mixing must be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of about 25 mm (29 inches) of mercury. The material will expand, crest and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. When using the RTV for potting, deaeration may be necessary after pouring to avoid trapping air in complex assemblies.

Automatic equipment designed to meter, mix, deaerate, and dispense two-component RTV silicone rubber compounds will add convenience to continuous or large volume operations. For additional information, refer to Momentive Performance Materials publication CDS1758.

### Curing

RTV12A mixed with RTV12C curing agent will gel in approximately two hours at room temperature. This permits handling a potted container without spilling the contents (even if inverted). However, complete cure requires 72 hours at room temperature.

More rapid cure may be realized by using mild heat. For example, cure may be obtained in one hour at 85°C (185°F). Laboratory curing tests should be run prior to production to determine the appropriate cure for a specific potted assembly. Longer cure times may be required for large and deep section assemblies.

### Bonding

RTV12 offers primerless adhesion to many components, wire insulation and potting containers used in electrical and electronic assemblies. To achieve optimum adhesion, all components must be clean and dry prior to potting. A laboratory test is recommended to confirm adhesion prior to production use. SS4004, SS4044 or SS4179 primers may improve RTV12 rubber adhesion to substrates showing borderline adhesion. Complete information and usage instructions for primers is available upon request. Bonding to components is desirable to minimize electrical leakage, particularly in humid environments.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Availability

RTV12A compound and RTV12C curing agent may be ordered from Momentive Performance Materials, Waterford, New York 12188, the Momentive Performance Materials sales office nearest you or an authorized Momentive Performance Materials distributor.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

**Contact Information** For product prices, availability, or order placement, contact our customer service by visiting [momentive.com/ContactSilicones](http://momentive.com/ContactSilicones).

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Holdings Inc.**

**DISCLAIMER**The information provided herein was believed by Momentive Performance Materials Inc. ("Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Momentive are subject to Momentive's terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE.** except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.