

RTV410, RTV420, RTV428

Versatile, High Strength, Low Viscosity Mouldmaking Materials Catalysts Beta 7 & Beta 8

Product Description

The RTV410, RTV420 and RTV428 are condensation cure mould-making materials that cure with Beta 7 or Beta 8 catalysts at room temperature to a high strength, flexible rubber. The RTV grades differ in mechanical properties, which allow users to select the optimum product that suits the individual needs.

Beta 7 is the general purpose catalyst.

Beta 8 is used for applications that require fast demoulding.

Key Performance Properties

- High tear resistance
- Long service life
- Chemical resistance
- Easy mould release
- Compatible with most moulding materials
- Excellent detail reproduction
- Room temperature cure
- Broad product range to suit individual needs

Applications

The RTV410, RTV420 and RTV428 condensation cure products have good flow, high flexibility and high tear strength ensuring good detail reproduction and long service life. When long work life is preferred Beta 7 is the catalyst of choice. Beta 8 is recommended for applications that require a fast demoulding time.

RTV410, RTV420 and RTV428 have excellent compatibility with most types of master pattern materials including rubber, wood, metal, clay and plastics as well as with reproduction materials as polyesters, epoxy, polyurethane, low melt alloys, wax, plaster, concrete and many other composite products.

The variation in hardness, viscosity, elongation, work life and demoulding time makes it possible for the user to select the optimal product that suits the user's needs. The RTV410, RTV420 and RTV428 compounds are recommended for use in mouldmaking applications where extreme flexibility is required such as soft printing pads for ink transfer, patterns for one piece moulding and skin moulding.



**Typical
Product
Data**

Typical uncured properties:

Base Compounds		RTV 410	RTV 420	RTV 428
Colour		Off White	Off White	Off White
Density	g/cm ³	1.28	1.24	1.30
Viscosity Brookfield	mPa·s	25.000	30.000	35.000
		Catalysts		
Property		Beta 7	Beta 8	
Colour		Translucent	Translucent	
Density	g/cm ³	0.96	0.96	
Viscosity Brookfield	mPa·s	28	28	
Mix ratio RTV 4xx : Beta		100 : 5	100 : 2.5	

Typical mixed properties:

Mix ratios by weight: RTV: Beta 7 is 100: 5. RTV : Beta 8 is 100 : 2.5

Pot life with Beta 7 : 75 minutes, cure time 24 hours

Pot life with Beta 8 : 10 minutes, cure time : 4 hours

Typical cured properties:

Cured with beta 7 at mix ratio 100:5. Data obtained on 2 mm sheet after 24 hr RT cure. Properties with Beta 8 will be comparable.

Property	RTV 410	RTV 420	RTV 428
Hardness (Shore A)	10	20	28
Tensile strength, MPa	2.6	3.3	3.2
Elongation @ break, %	750	600	450
Tear Strength (N/mm)	15	22	22
Linear shrinkage (%)	0.6	0.6	0.6

Specifications

Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV1/ RTV2.

Instructions for Use It is recommended to homogeneously mix the base compounds before use.

Mixing:

Select a mixing container 4-5 times larger than the total volume of material to be mixed. Weigh out the selected RTV and beta catalyst. Stir for several minutes scraping the sides and bottom of the container carefully to produce a homogeneous mixture. When using power mixers, avoid excessive speeds, which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

The air entrapped in the mixing step needs to be removed to eliminate voids in the cure product. This can be done by exposing the material to a vacuum of 10-20 mbar. The material will expand, crest and reduce to about the original level. Degassing is usually complete about two minutes after frothing ceases.

Automatic equipment designed to meter, mix and dispense a two-component silicone liquid elastomer will add convenience to continuous large scale operations.

Curing:

After mixing the selected RTV/Beta combination, the material will cure at room temperature. Selection of the Beta will determine cure speed, the work life as well as the demoulding time.

The system is sensitive to changes in heat and humidity and therefore variations in cure speed may be seen if one or both variables are changed.

Handling and Safety

Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.

Storage and Warranty Period

The warranted shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers below 27° C.

Availability

RTV410, RTV420 and RTV428 all are available in pails of 5 and 20 kg as well as in drums of 200 kg.

Beta 7 is available in bottles of 50 and 250 ml as well as in containers of 1 and 10 kg.

Beta 8 is available in a bottle of 500 ml.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constância Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	<ul style="list-style-type: none"> • Specialty Fluids • UA, Silanes, Resins, and Specialties • RTV Products-Elastomers • Sealants and Adhesives & Construction 	T 800.523.5862 T 800.334.4674 T 800.332.3390 T 877.943.7325	F 304.746.1654 F 304.746.1623 F 304.746.1623 F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	<ul style="list-style-type: none"> • Argentina & Chile • Brazil • Mexico & Central America • Venezuela, Ecuador, Peru, Colombia, & Caribbean 	T +54.11.4862.9544 T +55.11.4534.9650 T +52.55.5899.5135 T +58.212.285.2149	F +54.11.4862.9544 F +55.11.4534.9660 F +52.55.5899.5138 F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
Pacific	E cs-ap.silicones@momentive.com		
	<ul style="list-style-type: none"> • Japan • China • Korea • Singapore 	T +81.276.20.6182 T +86.21.5050.4666 (ext. 1523) T +82.2.6201.4600 T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS.

EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.