



RTV9910

RTV9910

Description

Several different curing agents are available for two-component RTV silicone rubber compounds to provide a choice of cure speed, mixing ratio, or deep section cure. DBT (dibutyl tin dilaurate) and STO (stannous tin octoate) are clear, easily pourable liquids, while white RTV9950 and beige RTV9910 are pastes and beige RTV9811 is a pourable paste. All are based on metal soaps. These curing agents are appropriate to use with the following Momentive Performance Materials products: RTV11, RTV21, RTV31, RTV41, RTV60, RTV77, RTV88, RTV511, RTV560, and RTV577.

Key Features and Benefits

DBT and STO

Simple handling procedures for easy use and low processing cost. Adjustable work time and cure rate obtainable through choice of curing agent and level used

RTV9910 and RTV9950

Convenient 10:1 mixing ratio for use in automatic dispensing or hand operations. Excellent colour contrast with red RTV base compounds provides visual evidence of complete mixing. RTV9910 provides extended pot life over RTV9950.

RTV9811

Convenient 10:1 mixing ratio for use in automatic dispensing or hand operations. Good colour contrast with RTV base compounds provides visual evidence of complete mixing. Good cure in deep sections eliminates need for multiple pours and long cure times. Inhibitor to prevent copper corrosion permits use with sensitive metals.

Typical Physical Properties

DBT, STO, RTV9811, RTV9910 and RTV9950 curing agents are appropriate to use with the following Momentive Performance Materials products: RTV11, RTV21, RTV31, RTV41, RTV60, RTV77, RTV88, RTV511, RTV560, and RTV577.

The curing agents have the following typical product properties:

	<i>DBT</i>	<i>STO</i>	<i>RTV9811</i>	<i>RTV9910</i>	<i>RTV9950</i>
Colour	Clear	Clear	Beige	Beige	White
Consistency	Liquid	Liquid	Pourable paste	Paste	Paste
Cure Speed	Moderate	Fast	Moderate	Slow	Moderate
Addition level (%)	0.1-0.5	0.1 - 0.5	5-10	10	5-10
Density, g/cm ³			1.50	1.80	1.75

Potential Applications

DBT(dibutyl tin dilaurate) is the liquid curing agent generally preferred for most applications. Used in concentrations from 0.1 to 0.5% by weight, DBT provides adequate work time and moderate cure speed. The effects of varying DBT concentration are shown in the table of typical cure rates. Varying the concentration within the limits shown has little or no effect upon the final cured properties of the RTV silicone rubber compound. STO (stannous tin octoate) is the fastest of the commonly used curing agents and is especially useful where cure times of one hour or less are required. Normally concentrations up to 0.5% by weight are used. Because of the short work time and rapid curing action, RTV silicone rubber compounds catalyzed with STO should be applied immediately after thorough mixing.

RTV9910 and RTV9950, a pre-blended paste based on DBT, is designed for use at a level of ten percent by weight of the RTV base compound. This ratio makes this product especially useful where automatic mixing and dispensing is needed for production line or large volume operations. At the ten percent level RTV9950 provides the equivalent of 0.5% DBT where the use of RTV9910 at ten percent will result in a longer worklife. RTV9811 has been specially designed for thorough cure of RTV silicone rubber compounds in thick section. This curing agent is also used at a level of ten percent by weight of the RTV base compound and is suggested for general use because of the easy mixing ratio, good colour contrast, and ability to cure in deep sections.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

CAUTION!

DBT, STO, RTV9950, and RTV9811 curing agents cause eye irritation and may cause skin irritation. Avoid contact with skin and eyes. In case of eye contact, flush with water for 15 minutes and see a physician. For skin contact, wash with soap and water. Clothing contaminated with DBT or STO should be removed and laundered before reuse.

The warranted shelf life of DBT, STO, RTV9910, RTV9950 and RTV9811 will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers below 27° C.

At temperatures below 18°C, the DBT curing agent may solidify warm gently to liquefy before using.

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

Mixing

Select a mixing container 4-5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out the silicone rubber base compound and add the appropriate amount of curing agent. With clean tools, thoroughly mix the RTV base compound and the curing agent, scraping the sides and bottom of the container carefully to produce a homogeneous mixture. When using power mixers, avoid excessive speeds which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

Deaeration

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of appr. 10 - 20 mbar. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. When using RTV silicone rubber for potting, a deaering step may be necessary after pouring to avoid capturing air in complex assemblies.

Automatic equipment designed to meter, mix, deaerate and dispense twocomponent RTV silicone rubber compounds will add convenience to continuous or large operations.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Availability

DBT is available in packages of 2.8, 28 and 113 gram. STO is available in packages of 113 and 407 gram. RTV9811 is available in packages of 454 gram and 2.27 and 22.7 kg. RTV9910 is available in packages of 454 gram and 2.27 kg. RTV9950 is available in package of 454 gram.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

Contact Information For product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Holdings Inc.

DISCLAIMER The information provided herein was believed by Momentive Performance Materials Inc. ("Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Momentive are subject to Momentive's terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE,** except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.