



TSE3051

TSE3051

Description

TSE3051 is a one-component, low viscosity silicone potting gel designed for electronic potting applications. This product cures with heat in a short period of time to a soft, tacky gel used to protect delicate electronic assemblies from humidity, dirt, and vibration.

TSE3051 is available in two colours: **TSE3051** Transparent **TSE3051-G** Light grey

Key Features and Benefits

KEY FEATURES

- Easy to use - one component, no mixing required, long pot life
- Low viscosity - pours easily, penetrates complex assemblies
- Fast heat cure system and heat accelerated cure
- Soft, tacky, sticky gel
- Absorbs shock and protects delicate mechanical components from vibration

TYPICAL APPLICATIONS

- Electrical and electronic potting such as hybrid IC insulation potting
- Power devices such as power module potting
- Mechanical cushioning and vibration damping material for delicate assemblies

Typical Physical Properties

UNCURED PROPERTIES		
Appearance		Transp. or light grey liquid
Viscosity (23°C)	Pa•s	0.7
Density (23°C),	g/cm ³	0.97
CURED PROPERTIES (2hrs @ 125°C)		TSE 3051
Penetration ASTM D 1403, 1/4 cone	1/10mm	85
Volume Resistivity	Ω • cm	1.0 x 10 ¹⁵
Storage shear modulus (G') *1	Pa(dyn/cm ²)	450 (4500)
Loss shear modulus (G'') *1	Pa(dyn/cm ²)	170 (1700)
Loss tangent (tans = G''/G')		0.4
Poissons ratio		0.5
Specific heat	J/(g.K)	1.51
Thermal Conductivity	W / m • K	0.17
Dielectric Strength	kV/mm	18
Dielectric Constant (60 Hz)		2.8
Dielectric Loss (60Hz)		0.001
Water Absorption ASTM D 570	%	0.05
Moisture permeability *2	g/m ² .24 hrs.	110
Volume Expansion	1/°C	1.0 x 10 ⁻³

*1 : 10rad/s at 25 °C*2 JIS Z 0208

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

Compatibility

TSE3051 silicone potting gel will cure in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a greasy appearance of the TSE3051 silicone potting gel at the interface between the gel and the substrate to be bonded. It is recommended that a sample patch test should be performed with the TSE3051 silicone potting gel to determine substrate compatibility.

Surface Preparation

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of TSE3051 silicone potting gel and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the gel.

Bonding

TSE3051 silicone potting gel offers outstanding adhesion characteristics to a wide variety of different substrates without the need of a primer. For difficult-to-bond-to substrates, or where more aggressive chemical adhesion is desired, the adhesion may be enhanced by using SS4155 silicone primer, available from Momentive Performance Materials. To apply the primer, thoroughly clean the surface and let dry. Then apply a uniform film (0.01- 0.02 mm) of SS4155 silicone primer and allow the primer to air-dry for one hour or more.

Curing

TSE3051 silicone potting gel requires the use of elevated temperatures in order to achieve full cure. Typical cure times and temperatures are as follows:

125°C	2 hours
150°C	1 hour
200°C	5 minutes

The actual cure time is affected by such things as cross-sectional thickness of the TSE3051 silicone potting gel, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared).

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Availability

TSE3051 is available in 1 kg cans and 20 kg pails. TSE3051G is available in 20 kg pails

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

Contact InformationFor product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Holdings Inc.

DISCLAIMERThe information provided herein was believed by Momentive Performance Materials Inc. ("Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Momentive are subject to Momentive's terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.