



# TSE326

## TSE326

### Description

TSE326 is a one-component, heat curing silicone adhesive which offers extended performance at temperatures exceeding 200C. A flowable material with primerless adhesion to many substrates, it is suitable for assembly and gasketing where a flowable consistency is required. TSE 326 requires a minimum cure temperature of 100C and offers very low linear shrinkage and an improved thermal conductivity of 0.29 W/m K. Reddish brown in color.

### Key Features and Benefits

- One component product-no mixing required
- Fast cure at elevated temperatures
- Primerless adhesion to many types of substrates
- Low linear shrinkage
- Excellent heat resistance
- Outstanding dielectric properties

### Typical Physical Properties

<b>Uncured Properties</b>	
Color	Reddish brown
Viscosity, cps	28,000
<b>Cured Properties (cured 1 hour at 150C)</b>	
Specific Gravity	1.45
Hardness (JIS A)	43
Tensile Strength, psi (kgf/cm <sup>2</sup> )	498 (35)
Elongation, %	170
Adhesion, psi, (kgf/cm <sup>2</sup> ) (Al to Al)	284 (20)
Dielectric Strength, volts/mil	558
Dielectric Constant	3.3
Dissipation Factor	0.02
Volume Resistivity, ohm-cm	2x10 <sup>15</sup>
Linear Thermal Expansion Coefficient, cm/cm C	17x10 <sup>-5</sup>

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## Product Safety, Handling and Storage

### CAUTION

Uncured TSE 326 silicone adhesive can generate flammable hydrogen gas upon contact with acidic, basic, or oxidizing materials. Such contact should be avoided.

The warranty period for TSE 326 silicone adhesive is 6 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at or below 10C (50F).

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## Processing Recommendations

### Compatibility

TSE 326 silicone adhesive will cure in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a gummy appearance of the TSE 326 silicone adhesive at the interface between the adhesive and the substrate to be bonded. It is recommended that a patch test be performed with the TSE 326 silicone adhesive to determine substrate compatibility.

### Surface Preparation

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of TSE 326 silicone adhesive and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the adhesive.

### Bonding

TSE 326 silicone adhesive offers outstanding adhesion characteristics to a wide variety of different substrates without the need of a primer.

For difficult-to-bond substrates, or where more aggressive chemical adhesion is desired, the adhesion may be enhanced by using SS4155 silicone primer, available from Momentive Performance Materials. To apply the primer, thoroughly clean the surface and let dry. Then apply a uniform film (0.01-0.02 mm/ 0.5-1.0 mil) of SS4155 silicone primer and allow the primer to air dry for one hour or more. For more details on priming and adhesion, please refer to Momentive Performance Materials product data sheet on silicone primers (#1873).

### Curing

TSE 326 silicone adhesive requires the use of elevated temperatures in order to achieve full cure. Typical cure times and temperatures are as follows:

Temperature	TSE 326
100C	2 hours
125C	45 minutes
150C	30 minutes

The actual cure time is affected by such things as cross-sectional thickness of the TSE 326 silicones adhesive, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared). If an oven is used, it should be well ventilated.

## Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

**Contact Information** For product prices, availability, or order placement, contact our customer service by visiting [momentive.com/ContactSilicones](http://momentive.com/ContactSilicones).

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Holdings Inc.**

**DISCLAIMER** The information provided herein was believed by Momentive Performance Materials Inc. ("Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Momentive are subject to Momentive's terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE.** except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.